



BRICKFORM® Pro-Dye™

Quick-Dry Concrete Dye (Liquid Formulation)

BRICKFORM Pro-Dye is a translucent dye, designed to penetrate and color any cementitious surface. Pro-Dye dries quickly, reducing installation time and construction costs. In most cases, cleanup and sealing can be done in the same day. It is ideal for polished concrete and it can be to achieve dramatic results.

FEATURES

- Large Selection of Vivid Colors
- Easy-to-Spray-Apply
- Interior Use Only
- Dries Quickly
- VOC: 0

PRODUCT DESCRIPTION • BRICKFORM Pro-Dye penetrates the surface of newly cured or existing non-porous concrete, creating a layer of translucent color that dries quickly and will not chip, crack, or peel. The colors produced in each section of concrete will be unique with captivating, multi-colored intensities that become a permanent part of the concrete. Colors can be combined to create an unlimited number of color variations. When applied properly, Pro-Dye creates intense color that has a look similar to the mottling effect of acid stain. BRICKFORM Pro-Dye is packaged in liquid form to be mixed in proportion to acetone.

USES • Pro-Dye is designed to work with the BRICKFORM PROFESSIONAL CONCRETE POLISHING SYSTEM for the coloring process in polishing floors. BRICKFORM Pro-Dye is durable enough for commercial applications like restaurants, showrooms and retail spaces. It can be used to create vivid, new color for interior floors or concrete countertops. BRICKFORM Pro-Dye can also be used to correct areas where acid stains have little or no reaction on the concrete surface. Pro-Dye is excellent in vertical applications, stencils, and logos because it dries so quickly.

LIMITATIONS • BRICKFORM Pro-Dye is NOT suitable for exterior applications or interior applications exposed to direct sunlight. BRICKFORM Pro-Dye may not cover up all discolorations that exist on the concrete surface and cannot be used to cover petroleum-type products such as oil, grease, or gasoline. Pro-Dye is NOT recommended for porous surfaces that may produce little or no mottling effect. BRICKFORM Pro-Dye is not a final coating so a sealer must be applied.

COLORS • BRICKFORM Pro-Dye is available in 26 standard colors.

PACKAGING • BRICKFORM Pro-Dye is available in containers packaged to color the following:

Pro-Dye	Acetone
8-Ounce (.23 L) Bottle	1-gallon (3.785 L)

BRICKFORM Mottling and Penetrating Agent™ is available in 24-ounce (.70 L) containers with 20-ounces (.59 L) of material.

COVERAGE • BRICKFORM Pro-Dye will color approximately 200 - 600 square feet per gallon, per coat, depending on the application method and the porosity or finish of the concrete surface.

STORAGE • Store in a safe place, out of direct sunlight. Keep containers tightly sealed. DO NOT allow product to freeze. Shelf life for the liquid color is approximately 24 months. Shelf life for the Mottling and Penetrating Agent is approximately 12 months.

CAUTION • KEEP OUT OF REACH OF CHILDREN. Before using or handling, read the Material Safety Data Sheet and the Warning and Warranty statements included in this Technical Information Sheet. DO NOT TAKE INTERNALLY. Do not breathe vapors or mist. Use only with adequate ventilation and use a respirator when levels are above applicable limits. Avoid contact with skin and eyes. Wear eye goggles, gloves and apron to protect skin. Close container after each use. Use good hygiene when handling this product and wash and bathe after each use. Be sure to wash clothing after each use.

EQUIPMENT • BRICKFORM Acetone Pump-Sprayer™: This sprayer is specifically designed for applying BRICKFORM Pro-Dye dissolved in acetone. The acetone sprayer is available in three and a half gallon (13.24 L). BRICKFORM Tips Kit™: An optional five-component tips kit is available. This kit gives the applicator options for applying chemicals ranging from fine to coarse spray patterns. A check valve is included with the tip kit.

MOISTURE • If the concrete surface has visible signs of moisture, Brickform recommends testing the slab by using a calcium chloride or a relative humidity test. Check to see if the slab was constructed, using a vapor barrier or retarder. Acceptable moisture levels should not exceed an average of 5-7 pounds per 1000 square feet MVER (Moisture Vapor Emissions Rate).

PREPARATION OF CONCRETE • BRICKFORM strongly recommends representative jobsite samples. Mock ups should always be prepared on the same concrete that the dye is to be applied. Individuals who will be performing the work should test different sections of the concrete to determine suitability, coverage of the dye and final appearance. The concrete should be cured at least 28 days. The application area must be completely free of sealers, oils, dirt, paint, alkali, penetrating sealers, or any foreign materials that would prevent BRICKFORM Pro-Dye from penetrating the concrete surface. The recommended substrate should have a minimum concrete surface profile (CSP) of one in accordance to the ICRI Guideline No. 03732. This guideline is available at www.icri.org. See surface preparation videos at www.brickform.com. Remove any BRICKFORM Liquid Release™ prior to application of the dye. Protect adjacent areas from over-spray, runoff, spills, and tracking, prior to application.

WARNING • Acetone will produce vapors that are highly flammable and may cause flash fires. Do not breathe vapors or mist. Acetone can be harmful if inhaled. Use only with ventilation sufficient to prevent exceeding recommended exposure limit or buildup of explosive concentrations of vapor in air. Use only MSHA or NIOSH approved atmosphere supplying or air purifying respirators in confined or enclosed spaces for organic vapors. Use explosion-proof equipment. Make certain no source of open flame is present. Pilot lights, heaters, cigarettes, and electric tools should not be in use or turned on until all vapors have dissipated. Use splash goggles or face shield to protect face and eyes. Use chemical-resistant gloves and avoid prolonged or repeated skin contact. **KEEP OUT OF REACH OF CHILDREN.**

MIXING • BRICKFORM Pro-Dye is packaged in liquid form and needs to be mixed with acetone. Please follow the Acetone manufacturer's instructions and Material Safety Data Sheet (MSDS) for safe handling and exposure limits. Mix one bottle of Pro-Dye to one gallon of acetone. This can be done by simply adding the Liquid into the acetone container. Close the acetone container and shake the contents for approximately 30 seconds. Pro-Dye colors can be combined to create an unlimited number of color variations. Once mixed Pro-Dye is ready for application.

BRICKFORM Mottling & Penetrating Agent™ can be used with BRICKFORM Pro-Dye in the following amounts to increase the mottling effect and slow drying time and increase permeability:

Acetone Container Size: BRICKFORM Mottling and Penetrating Agent:

1 Gallon	Add 4 Ounces
5 Gallons	Add 20 Ounces

Add the Mottling and Penetrating Agent at anytime prior to the application. Be sure to mix thoroughly by shaking or stirring for approximately 30 seconds.

DO NOT USE any type of electrical equipment to stir the product into the Acetone. Acetone is highly flammable and may ignite. Do not use Brickform Mottling and Penetrating Agent if the application is for stencils or vertical surfaces or other uses where the product needs to dry quickly. **NOTE: BRICKFORM Mottling & Penetrating Agent is not recommended with porous or broom-finished concrete.**

APPLICATION • Pro-Dye is ready for application as soon as it's mixed with acetone. Begin by spraying evenly and continuously over the prepared surface, using a #6 or #8 tip or equivalent, in a circular motion. Do not allow the Pro-Dye to puddle. Mop up any excess with a clean rag so that the surface will dry evenly.

Do not track dye onto pavement that is to remain uncolored. If using Pro-Dye in a polishing system, Continue with the Lythic Densifier and Lythic Guard for the rest of the polishing process. Read the Lythic Densifier and Guard products TIS before application.

SEALING • DO NOT USE A SEALER ON A POLISHED FLOOR. BRICKFORM Pro Concrete Guard should be used for protection and maintenance of the polished floor.

The recommended surface profile for BRICKFORM sealers is a CSP1 or CSP2. Allow Pro-Dye to thoroughly dry (approximately 1 minute) and then clean thoroughly before applying a sealer. It is recommended that the applicator dry-buff with a white pad using a buffer or burnisher and remove loose dye with vacuum or dust mop. **DO NOT USE** water to clean the surface. This will cause the residue to float onto unwanted areas.

After Pro Dye has been installed and all of the residue has been removed spray one of the following sealers on the project with a pump up type sprayer or an airless type sprayer. **DO NOT ROLL ON THE SEALER OR IT WILL LIFT THE COLOR.** Protect the surface with Gem-Seal™, Poly-Seal™, Safety-Seal™, UreMax™ or Poly-Astic™. After the sealer has been allowed to cure, protective coats of BRICKFORM Dura-Wax™ may be applied on interior projects to prolong the life of the sealer. Please get a copy of the appropriate Technical Information and Material Safety Data Sheet before attempting to use these products.

MAINTENANCE • For maintenance on a polished floor apply Lythic cleaner depending on the amount and type of traffic. (See Lythic Cleaner TIS before application).

The sealed surface should be inspected periodically for areas of thin or traffic-worn wax or sealer. Reapply as needed, according to the appropriate Technical Information Sheet. If traces of efflorescence are present, all wax and sealer should be removed and the efflorescence eliminated with a gentle cleaner such as BRICKFORM E-Etch™, according to the *BRICKFORM E-Etch Technical Information Sheet*.

WARRANTY • This product is not intended for public use and is intended for use by licensed contractors and installers, experienced and trained in the use of these products. It is warranted to be of uniform quality, within manufacturing tolerances. The manufacturer has no control over the use of this product, therefore, no warranty, expressed or implied, is or can be made either as to the effects or as results of such use. In any case, the manufacturer's obligations shall be limited to refunding the purchase price or replacing material proven defective. The end user shall be responsible for determining product's suitability and assumes all risks and liability.

PLAN SPECIFICATION

BRICKFORM® Pro-Dye™ Suggested Short Form Specification:

All concrete surfaces designated in the plans and specifications as being dyed with a dye, shall receive one application of BRICKFORM Pro-Dye, in _____ color, after the concrete has cured a minimum of approximately 28 days. The surface shall be prepared and BRICKFORM Pro-Dye applied in accordance with the *BRICKFORM Pro-Dye Technical Information Sheet*, using the minimum coverage rate. For concrete Polishing, Pro-Dye should be used with BRICKFORM Pro Lithium Densifier and Pro Concrete Guard. All dyed surfaces (non-polished) shall be sealed with Gem-Seal™, Poly-Seal™, Safety-Seal™, UreMax™ or Poly-Astic™ in accordance with the corresponding Technical information Sheet. All products shall be manufactured by BRICKFORM, 800-483-9628, Rialto, CA.

ORDER SPECIFICATIONS

Product

Pro-Dye

Shipping Weight:

2.5-ounces (.07 kg)

Part Number

DSL- 110

DSL- 210

DSL- 310

DSL- 410

DSL- 510

DSL- 610

DSL- 710

DSL- 810

DSL- 910

DSL- 1100

DSL- 2010

DSL- 2210

DSL- 2510

DSL- 2710

DSL- 3010

DSL- 3510

DSL- 3710

DSL- 4010

DSL- 4210

DSL- 4510

DSL- 5010

DSL- 5210

DSL- 5510

DSL- 6710

DSL- 7010

DSL- 7210

Container Size

8 ounces (.23 L)

Color

Jade

Turquoise

Coffee

Caramel

Mahogany

Ebony

Mission Brown

Amber

Olive

Walnut

Gold

Raw Sienna

Deep Caramel

Sand

Terra Cotta

Chocolate Brown

Saddle Brown

Deep Walnut

Burnt Sienna

Chestnut

Sepia

Eggplant

Patriot Blue

Forest Green

Midnight Black

Black

Colors Acetone

1-gallon (3.785 L)

Product

Mottling & Penetrating Agent (MPA)

Part Number

DS-8000

Product

Tip Kit with Check Valve

Shipping Weight:

18 ozs (.02 kg)

Part Number

DS-8500

Container Size

24-ounces (.70 L)

Shipping Weight:

4 Ounces (.02 kg)

Polishing System:

Pro Lithium Densifier

Pro Concrete Guard

Part No. CP-1305

Part No. CP-1205